

APPLICATION NOTE

Measurements in Polyurethanes Using NIR Spectroscopy

Polyurethanes are one of the most Polyurethanes are one of the most versatile polymers available. Polyurethanes can be a found in liquid coatings and paints, elastomers, rigid insulation, soft flexible foam, elastic fiber, and many other materials. Today, polyurethanes can be found in virtually everything we touch – our desks, chairs, cars, clothes, footwear, appliances, beds, the insulation in our walls, roof and moldings on our homes. Polyurethanes are made by reacting diisocyanates with dialcohols (Figure 1).

Many aspects of polyurethane production can be measured using Near-Infrared (NIR) spectroscopy. This application note will describe the potential uses of our GUIDED WAVE™ hardware and software tools for key measurements in polyurethane production using fiber optic based NIR spectroscopy. GUIDED WAVE analyzer systems use fiber optics to allow the sample probe to be located in remote locations away from the spectrophotometer itself. NIR spectroscopic methods can be applied in real time directly in process monitoring or as laboratory procedures. In either case NIR is a time and money saving alternative to traditional methods. NIR also offers the benefit of increased safety over traditional methods. A specific publication on the use of NIR to measure hydroxyl content of polyols can be found in the Application Note Hydroxyl Number in Polyols.

$$^{HO}_{R}$$
 OH + $O=\underline{-}N-R'-N=\underline{-}O$ \longrightarrow

$$\begin{array}{c|c} \bullet & \bullet & \bullet \\ \hline \bullet & \bullet - R - O \\ \hline & N - R' - N \\ & O \\ & H \end{array} \begin{array}{c} O - R - O \\ & N - R' - N \\ & O \\ & O \end{array} \begin{array}{c} O - R - O \\ & N - R' - N \\ & O \\ & O \end{array} \begin{array}{c} O - R - O \\ & O \\ & O \end{array}$$

Figure 1: Polyurethane Reaction

Measurement Background

For The NIR region of the electromagnetic spectrum has absorbance bands resulting from overtones and combinations of the C-H, O-H, and N-H fundamental bands in the mid infrared. Typically, the NIR spectra of a series of samples of standards are used to generate a quantitative model that will be used to measure the composition (or property) in future samples based only on the sample's NIR spectrum. The initial model development step is the optimization of data preprocessing to improve model accuracy. These preprocessing steps are typically in the form of baseline correction or derivative calculation but may include more complex calculations. The pre-processed spectra and concentration or property data are then submitted to the thrid party software and a calibration model is developed using PLS regression methodology. For a discussion of PLS and other multivariate calibration techniques please see Martens & Naes¹ and ASTM E1655².

Polyurethane Raw Materials

Polyurethanes contain the repeating unit:

Polyurethanes are produced by a reaction of diisocyanates with dialcohols. As a simplified example of raw material measurement potential, the spectra of ortho and para tolyl-isocyanate were measured using both 2 and 10 mm path probes. The 10 mm path probe produces spectral data in the 1000 – 1600 nm region that would be suitable for quantitative measurements while the 2 mm path spectra have useful information in the extended NIR region of 1600 – 2000 nm. Which region proves to be most useful will depend on the property being measured and on the other materials present in the reaction. Figure 2 shows the isocyanate spectra using the 10 mm path probe in comparison to ortho and para chloro-toluene. This shows the isocyanate peak at approximately 1490 nm and some possible distinction between the isomers of the isocyanate. Figure 3 shows the spectra of the same materials using the 2 mm path probe extending the wavelength range out to 2050 nm. These spectra show similar distinctions, with a band due to the isocyante seen at approximately 1870 nm.




Figure 2: Isocyanates - 10 mm Pathlength - Short Wavelength NIR

Polyurethane Raw Materials (continued)

When considering final product measurements, polyurethanes can really be considered an amide or an ester of carbonic acid (carbamate). To examine this functional group, the spectrum of methyl and phenyl carbamate were measured. Figures 4 and 5 show the spectra of neat methyl carbamate, and phenyl carbamate at 10% concentration in acetone. Again, two pathlengths are used to show data in both the short and the long wavelength NIR regions.

The peaks arising from the carbamate are seen at 1475 nm and 1960 nm in the 10 mm and 2 mm pathlength spectra respectively. The wavelength separation between the isocyanate bands and the carbamate bands should be sufficient to allow quantitative measurements to be made when both are present.




Figure 3: Isocyanates - 2 mm Pathlength - Long Wavelength NIR




Figure 4: Carbamate - 10 mm Pathlength - Short Wavelength NIR




Figure 5: Carbamate - 2 mm Pathlength - Long Wavelength NIR

Conclusion

The measurement of OH number of polyols using NIR spectroscopy has been shown in earlier studies to be both fast and reliable utilizing our hardware and software tools. The data shown here indicates that additional measurements in polyurethane systems are feasible. The use of remote spectroscopic measurement methods provides analyses in real time and minimizes the need for performing laboratory measurements. These methods can be applied in reactor systems for control of important properties during the reaction and to determine the endpoint of the reaction thus adding to the value and cost savings. The accuracy of any such measurements would need to be studied in greater detail. For more detailed information regarding either further feasibility studies or system specifications please contact a Process Insights sales or technical specialist.

References

- 1. H. Martens, T. Naes, Multivariate Calibration, John Wiley & Sons, 1989.
- 2. ASTM E1655 Standard Practices for Infrared, Multivariate, Quantitative Analysis.



GAIN REAL-TIME INSIGHT INTO YOUR PROCESS

Process Insights manufactures and delivers premium sensors, monitors, detectors, analyzers, instrumentation, and software that are mission-critical to keep your operations, personnel, and the environment safe – every day across the globe.

Get the most reliable, precision analytical technologies available on the market today. We will work to match your needs and budget, and provide the optimal, and most stable process analysis solution for your application.

CENTERS OF EXCELLENCE | PROVIDING PROVEN SOLUTIONS

Process Insights is committed to solving our customers' most complex analytical, process, and measurement challenges everyday.

Process Insights - The Americas

4140 World Houston Parkway Suite 180, Houston, TX 77032, USA +1 713 947 9591

Process Insights - EMEA

ATRICOM, Lyoner Strasse 15, 60528 Frankfurt, Germany +49 69 20436910

Process Insights - APAC

Wujiang Economic and Technology, Development Zone, No. 258 Yi He Road, 215200 Suzhou, Jiangsu Province, China +86 400 086 0106

For a complete range of products, applications, systems, and service options, please contact us at: info@process-insights.com

For a complete list of sales & manufacturing sites, please visit: https://www.process-insights.com/about-us/locations/

COSA Xentaur, Tiger Optics, Extrel, Alpha Omega Instruments, ATOM Instrument, MBW Calibration, MGA, Guided Wave, ANALECT and LAR TOC Leader are trademarks of Process Insights, Inc.



www.process-insights.com Copyright © 2023 Process Insights, Inc. All Rights Reserved.